

RCH-COATED SOLID CARBIDE  
**DREAM DRILL X without COOLANT HOLES (3XD)**

SERIES  
**NEW DTX423**

- ▶ Upgraded coating for higher Tool Life in various materials
- ▶ Soft cutting action and reduced axial forces; Easy to Recondition
- ▶ Good self-centering even at low feed rates and unstable situations
- ▶ Excellent Chip breaking and chip evacuation



DIN 6537 CARBIDE 30° h6 m7 140° RCH Coating p.40

**SHORT**  
3 × D

Unit : mm

EDP No.	Drill Diameter	Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter	Shank Diameter	Flute Length	Overall Length
RCH-Coating	D1	D2	L1	L2	RCH-Coating	D1	D2	L1	L2
DTX423030	3.0	6	20	62	DTX423060	6.0	6	28	66
DTX423031	3.1	6	20	62	DTX423061	6.1	8	34	79
DTX423032	3.2	6	20	62	DTX423062	6.2	8	34	79
DTX423033	3.3	6	20	62	DTX423063	6.3	8	34	79
DTX423034	3.4	6	20	62	DTX423064	6.4	8	34	79
DTX423035	3.5	6	20	62	DTX423065	6.5	8	34	79
DTX423036	3.6	6	20	62	DTX423066	6.6	8	34	79
DTX423037	3.7	6	20	62	DTX423067	6.7	8	34	79
DTX423038	3.8	6	24	66	DTX423068	6.8	8	34	79
DTX423039	3.9	6	24	66	DTX423069	6.9	8	34	79
DTX423040	4.0	6	24	66	DTX423070	7.0	8	34	79
DTX423041	4.1	6	24	66	DTX423071	7.1	8	41	79
DTX423042	4.2	6	24	66	DTX423072	7.2	8	41	79
DTX423043	4.3	6	24	66	DTX423073	7.3	8	41	79
DTX423044	4.4	6	24	66	DTX423074	7.4	8	41	79
DTX423045	4.5	6	24	66	DTX423075	7.5	8	41	79
DTX423046	4.6	6	24	66	DTX423076	7.6	8	41	79
DTX423047	4.7	6	24	66	DTX423077	7.7	8	41	79
DTX423048	4.8	6	28	66	DTX423078	7.8	8	41	79
DTX423049	4.9	6	28	66	DTX423079	7.9	8	41	79
DTX423050	5.0	6	28	66	DTX423080	8.0	8	41	79
DTX423051	5.1	6	28	66	DTX423081	8.1	10	47	89
DTX423052	5.2	6	28	66	DTX423082	8.2	10	47	89
DTX423053	5.3	6	28	66	DTX423083	8.3	10	47	89
DTX423054	5.4	6	28	66	DTX423084	8.4	10	47	89
DTX423055	5.5	6	28	66	DTX423085	8.5	10	47	89
DTX423056	5.6	6	28	66	DTX423086	8.6	10	47	89
DTX423057	5.7	6	28	66	DTX423087	8.7	10	47	89
DTX423058	5.8	6	28	66	DTX423088	8.8	10	47	89
DTX423059	5.9	6	28	66	DTX423089	8.9	10	47	89

▶ Other shank types are available on your request.

▶ NEXT PAGE

◎ : Excellent ○ : Good

ISO	P										M				K										
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel				Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron				
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25
HRc	13	25	28	32	38	35	38	42	48	55	58	60	63	66	68	70	72	74	76	78	80	82	84	86	88
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230					
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

ISO	N										S						H							
	Aluminum-wrought alloy		Aluminum-cast alloyed			Copper and Copper Alloys (Bronze / Brass)		Non Metallic Materials			Heat Resistant Super Alloys			Titanium Alloys			Hardened steel	Chilled Cast Iron	Hardened Cast Iron					
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44
HRc	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550			
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

RCH-COATED SOLID CARBIDE  
**DREAM DRILL X without COOLANT HOLES (3XD)**

SERIES  
**NEW DTX423**

- ▶ Upgraded coating for higher Tool Life in various materials
- ▶ Soft cutting action and reduced axial forces; Easy to Recondition
- ▶ Good self-centering even at low feed rates and unstable situations
- ▶ Excellent Chip breaking and chip evacuation



DIN 6537 CARBIDE 30° h6 m7 140° RCH Coating p.40

**SHORT**  
3 × D

Unit : mm

EDP No.	Drill Diameter	Shank Diameter	Flute Length	Overall Length	EDP No.	Drill Diameter	Shank Diameter	Flute Length	Overall Length
RCH-Coating	D1	D2	L1	L2	RCH-Coating	D1	D2	L1	L2
DTX423090	9.0	10	47	89	DTX423120	12.0	12	55	102
DTX423091	9.1	10	47	89	DTX423123	12.3	14	60	107
DTX423092	9.2	10	47	89	DTX423125	12.5	14	60	107
DTX423093	9.3	10	47	89	DTX423128	12.8	14	60	107
DTX423094	9.4	10	47	89	DTX423130	13.0	14	60	107
DTX423095	9.5	10	47	89	DTX423135	13.5	14	60	107
DTX423096	9.6	10	47	89	DTX423138	13.8	14	60	107
DTX423097	9.7	10	47	89	DTX423140	14.0	14	60	107
DTX423098	9.8	10	47	89	DTX423145	14.5	16	65	115
DTX423099	9.9	10	47	89	DTX423148	14.8	16	65	115
DTX423100	10.0	10	47	89	DTX423150	15.0	16	65	115
DTX423101	10.1	12	55	102	DTX423155	15.5	16	65	115
DTX423102	10.2	12	55	102	DTX423158	15.8	16	65	115
DTX423103	10.3	12	55	102	DTX423160	16.0	16	65	115
DTX423104	10.4	12	55	102	DTX423165	16.5	18	73	123
DTX423105	10.5	12	55	102	DTX423168	16.8	18	73	123
DTX423106	10.6	12	55	102	DTX423170	17.0	18	73	123
DTX423107	10.7	12	55	102	DTX423175	17.5	18	73	123
DTX423108	10.8	12	55	102	DTX423178	17.8	18	73	123
DTX423109	10.9	12	55	102	DTX423180	18.0	18	73	123
DTX423110	11.0	12	55	102	DTX423185	18.5	20	79	131
DTX423111	11.1	12	55	102	DTX423190	19.0	20	79	131
DTX423112	11.2	12	55	102	DTX423195	19.5	20	79	131
DTX423113	11.3	12	55	102	DTX423198	19.8	20	79	131
DTX423114	11.4	12	55	102	DTX423200	20.0	20	79	131
DTX423115	11.5	12	55	102					
DTX423116	11.6	12	55	102					
DTX423117	11.7	12	55	102					
DTX423118	11.8	12	55	102					
DTX423119	11.9	12	55	102					

▶ Other shank types are available on your request.

◎ : Excellent ○ : Good

ISO	P										M				K										
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel				Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron				
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25
HRc	13	25	28	32	38	35	38	42	48	55	58	60	63	66	68	70	72	74	76	78	80	82	84	86	88
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230					
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

ISO	N										S						H							
	Aluminum-wrought alloy		Aluminum-cast alloyed			Copper and Copper Alloys (Bronze / Brass)		Non Metallic Materials			Heat Resistant Super Alloys			Titanium Alloys			Hardened steel	Chilled Cast Iron	Hardened Cast Iron					
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44
HRc	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41	42	43	44
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550			
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

**DTX404, DTX423, DTX424** SERIES

without COOLANT HOLES

Vc = m/min.  
RPM = rev./min.  
FEED = mm/rev.

ISO	VDI 3323	Material Description	Vc	Parameter	Drill Diameter (mm)					
					1.0	2.0	3.0	4.0	5.0	6.0
P	2	Non-alloy steel	70	RPM	22280	11140	10610	7960	6370	5310
				FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
				RPM	22280	11140	10610	7960	6370	5310
	3	Non-alloy steel	70	RPM	22280	11140	10610	7960	6370	5310
				FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
				RPM	22280	11140	10610	7960	6370	5310
	4	Non-alloy steel	70	RPM	22280	11140	10610	7960	6370	5310
				FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
				RPM	22280	11140	10610	7960	6370	5310
	5	Non-alloy steel	70	RPM	19100	9550	8490	6370	5090	4240
				FEED	0.03-0.05	0.05-0.07	0.04-0.10	0.07-0.13	0.10-0.16	0.12-0.18
RPM				19100	9550	8490	6370	5090	4240	
6	Low alloy steel	70	RPM	22280	11140	10610	7960	6370	5310	
			FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22	
			RPM	19100	9550	8490	6370	5090	4240	
7	Low alloy steel	60	RPM	19100	9550	8490	6370	5090	4240	
			FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22	
			RPM	19100	9550	8490	6370	5090	4240	
8	Low alloy steel	60	RPM	19100	9550	8490	6370	5090	4240	
			FEED	0.02-0.04	0.03-0.05	0.04-0.10	0.07-0.13	0.10-0.16	0.12-0.18	
			RPM	9550	4770	4240	3180	2550	2120	
9	Low alloy steel	30	RPM	9550	4770	4240	3180	2550	2120	
			FEED	0.02-0.04	0.03-0.05	0.03-0.08	0.05-0.11	0.08-0.14	0.10-0.16	
			RPM	15920	7960	7430	5570	4460	3710	
10	High alloyed steel, and tool steel	50	RPM	15920	7960	7430	5570	4460	3710	
			FEED	0.03-0.05	0.05-0.07	0.04-0.10	0.07-0.13	0.10-0.16	0.12-0.18	
			RPM	9550	4770	4240	3180	2550	2120	
11	High alloyed steel, and tool steel	30	RPM	9550	4770	4240	3180	2550	2120	
			FEED	0.02-0.04	0.03-0.05	0.03-0.08	0.05-0.11	0.08-0.14	0.10-0.16	
			RPM	15920	7960	7430	5570	4460	3710	
M	12	Stainless steel	50	RPM	15920	7960	7430	5570	4460	3710
				FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
M	13	Stainless steel	35	RPM	11140	5570	4770	3580	2860	2390
				FEED	0.02-0.04	0.03-0.05	0.04-0.10	0.07-0.13	0.10-0.16	0.12-0.18
K	15	Grey cast iron	70	RPM	22280	11140	10610	7960	6370	5310
				FEED	0.04-0.06	0.04-0.06	0.08-0.14	0.12-0.18	0.15-0.22	0.20-0.26
	16	Grey cast iron	65	RPM	20690	10350	8490	6370	5090	4240
				FEED	0.04-0.06	0.04-0.06	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
	17	Nodular cast iron	70	RPM	22280	11140	10610	7960	6370	5310
				FEED	0.04-0.06	0.04-0.06	0.08-0.14	0.12-0.18	0.15-0.22	0.20-0.26
	18	Nodular cast iron	50	RPM	15920	7960	7430	5570	4460	3710
				FEED	0.04-0.06	0.04-0.06	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
	19	Malleable cast iron	60	RPM	19100	9550	8490	6370	5090	4240
				FEED	0.04-0.06	0.04-0.06	0.08-0.14	0.12-0.18	0.15-0.22	0.20-0.26
20	Malleable cast iron	50	RPM	15920	7960	7430	5570	4460	3710	
			FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22	
H	38	Hardened steel	20	RPM	6370	3180	2650	1990	1590	1330
				FEED	0.01-0.02	0.01-0.03	0.01-0.03	0.01-0.04	0.02-0.05	0.03-0.06

ISO	VDI 3323	Material Description	Vc	Parameter	Drill Diameter (mm)							
					8.0	10.0	12.0	14.0	16.0	18.0	20.0	
P	2	Non-alloy steel	100	RPM	3980	3180	2650	2270	1990	1770	1590	
				FEED	0.18-0.24	0.19-0.27	0.21-0.29	0.23-0.31	0.25-0.33	0.28-0.38	0.30-0.40	
				RPM	3980	3180	2650	2270	1990	1770	1590	
	3	Non-alloy steel	100	RPM	3980	3180	2650	2270	1990	1770	1590	
				FEED	0.18-0.24	0.19-0.27	0.21-0.29	0.23-0.31	0.25-0.33	0.28-0.38	0.30-0.40	
				RPM	3980	3180	2650	2270	1990	1770	1590	
	4	Non-alloy steel	100	RPM	3980	3180	2650	2270	1990	1770	1590	
				FEED	0.14-0.20	0.15-0.23	0.17-0.25	0.18-0.26	0.19-0.27	0.20-0.30	0.22-0.32	
				RPM	3180	2550	2120	1820	1590	1410	1270	
	5	Non-alloy steel	80	RPM	3180	2550	2120	1820	1590	1410	1270	
				FEED	0.14-0.20	0.15-0.23	0.17-0.25	0.18-0.26	0.19-0.27	0.20-0.30	0.22-0.32	
RPM				3980	3180	2650	2270	1990	1770	1590		
6	Low alloy steel	100	RPM	3980	3180	2650	2270	1990	1770	1590		
			FEED	0.18-0.24	0.19-0.27	0.21-0.29	0.23-0.31	0.25-0.33	0.28-0.38	0.30-0.40		
			RPM	3180	2550	2120	1820	1590	1410	1270		
7	Low alloy steel	80	RPM	3180	2550	2120	1820	1590	1410	1270		
			FEED	0.18-0.24	0.19-0.27	0.21-0.29	0.23-0.31	0.25-0.33	0.28-0.38	0.30-0.40		
			RPM	3180	2550	2120	1820	1590	1410	1270		
8	Low alloy steel	80	RPM	3180	2550	2120	1820	1590	1410	1270		
			FEED	0.14-0.20	0.15-0.23	0.17-0.25	0.18-0.26	0.19-0.27	0.20-0.30	0.22-0.32		
			RPM	1590	1270	1060	910	800	710	640		
9	Low alloy steel	40	RPM	1590	1270	1060	910	800	710	640		
			FEED	0.12-0.18	0.13-0.19	0.14-0.20	0.15-0.21	0.16-0.22	0.17-0.25	0.18-0.28		
			RPM	2790	2230	1860	1590	1390	1240	1110		
10	High alloyed steel, and tool steel	70	RPM	2790	2230	1860	1590	1390	1240	1110		
			FEED	0.14-0.20	0.15-0.23	0.17-0.25	0.18-0.26	0.19-0.27	0.20-0.30	0.22-0.32		
			RPM	1590	1270	1060	910	800	710	640		
11	High alloyed steel, and tool steel	40	RPM	1590	1270	1060	910	800	710	640		
			FEED	0.12-0.18	0.13-0.19	0.14-0.20	0.15-0.21	0.16-0.22	0.17-0.25	0.18-0.28		
			RPM	2790	2230	1860	1590	1390	1240	1110		
M	12	Stainless steel	70	RPM	2790	2230	1860	1590	1390	1240	1110	
				FEED	0.18-0.24	0.19-0.27	0.21-0.29	0.23-0.31	0.25-0.33	0.28-0.38	0.30-0.40	
M	13	Stainless steel	45	RPM	1790	1430	1190	1020	900	800	720	
				FEED	0.14-0.20	0.15-0.23	0.17-0.25	0.18-0.26	0.19-0.27	0.20-0.30	0.22-0.32	
K	15	Grey cast iron	100	RPM	3980	3180	2650	2270	1990	1770	1590	
				FEED	0.22-0.28	0.25-0.33	0.27-0.35	0.29-0.37	0.31-0.39	0.32-0.42	0.34-0.44	
	16	Grey cast iron	80	RPM	3180	2550	2120	1820	1590	1410	1270	
				FEED	0.18-0.24	0.19-0.27	0.21-0.29	0.23-0.31	0.25-0.33	0.28-0.38	0.30-0.40	
	17	Nodular cast iron	100	RPM	3980	3180	2650	2270	1990	1770	1590	
				FEED	0.22-0.28	0.25-0.33	0.27-0.35	0.29-0.37	0.31-0.39	0.32-0.42	0.34-0.44	
	18	Nodular cast iron	70	RPM	2790	2230	1860	1590	1390	1240	1110	
				FEED	0.18-0.24	0.19-0.27	0.21-0.29	0.23-0.31	0.25-0.33	0.28-0.38	0.30-0.40	
	19	Malleable cast iron	80	RPM	3180	2550	2120	1820	1590	1410	1270	
				FEED	0.22-0.28	0.25-0.33	0.27-0.35	0.29-0.37	0.31-0.39	0.32-0.42	0.34-0.44	
20	Malleable cast iron	70	RPM	2790	2230	1860	1590	1390	1240	1110		
			FEED	0.18-0.24	0.19-0.27	0.21-0.29	0.23-0.31	0.25-0.33	0.28-0.38	0.30-0.40		
H	38	Hardened steel	25	RPM	990	800	660	570	500	440	400	
				FEED	0.03-0.06	0.04-0.07	0.04-0.08	0.05-0.09	0.05-0.09	0.05-0.10	0.05-0.10	

► Recommend to reduce the feed rate as following **Feed 100%** : DTX404(3×D), DTX423(3×D), DTX424(5×D)

**DTX406, DTX408, DTX421** SERIES

with COOLANT HOLES

Vc = m/min.  
RPM = rev./min.  
FEED = mm/rev.

ISO	VDI 3323	Material Description	Vc	Parameter	Drill Diameter (mm)					
					1.0	2.0	3.0	4.0	5.0	6.0
P	2	Non-alloy steel	80	RPM	25460	12730	11670	8750	7000	5840
				FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
				RPM	25460	12730	11670	8750	7000	5840
	3	Non-alloy steel	80	RPM	25460	12730	11670	8750	7000	5840
				FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
				RPM	25460	12730	11670	8750	7000	5840
	4	Non-alloy steel	80	RPM	25460	12730	11670	8750	7000	5840
				FEED	0.03-0.05	0.05-0.07	0.06-0.12	0.08-0.14	0.14-0.20	0.16-0.22
				RPM	22280	11140	9550	7160	5730	4770
	5									

**NEW**  
**DREAM DRILL X**

**New Coating Technology "RCH-Coating"**

Combining the major benefits of TiAlN and AlCrN into a new 'Nano Layered Multilayer' coating generation provides unique advantages such as:



Extreme Wear Resistance




High Heat Endurance



Chipping Protection

**↑ Tool Life**  
compared to Normal TiAlN coated drills  
**20 to 50%**




Nano Layered Multilayer  
Carbide

At insufficient coolant conditions where higher temperatures occur, **RCH-Coating** allows with its very high temperature stability for great tool life results.

**FEATURES & BENEFITS**


- **Universal Point Grinding**  
Soft cutting action and reduced axial forces; Easy to Recondition
- **Radius Thinning**  
Provides very good self centering even at low feed rates and unstable situations
- **Tailored Flute Design**  
Excellent chip breaking and evacuation
- **Edge Preparation**  
Maximizing tool life in various materials



**CASE STUDY**

► **SOLID CARBIDE DREAM DRILL X with Coolant Holes**

CUTTING CONDITION	
Work Material	• DIN : C45 • AISI : 1045 • JIS : S45C (HRc20)
Drill Diameter(mm)	Ø10.0
Cutting Speed	109.99 m/min.
Feed	0.23 mm/rev
Drilling Depth	40mm
Coolant	Internal Cooling Wet Cut (9% Emulsion)
Machine	Vertical Machine



**DREAM DRILL X**



Total Drilling 384 Holes

**Conventional Drill**



Total Drilling 384 Holes

► **SOLID CARBIDE DREAM DRILL X with Coolant Holes**

CUTTING CONDITION	
Work Material	• DIN : GGG40 • AISI : 60-40-18 • JIS : FCD400
Drilling Diameter(mm)	Ø8.5
Cutting Speed	112m/min
Feed	0.33mm/rev.
Drilling Depth	18mm
Coolant	Internal Cooling
Machine	Machining Center (Horizontal)

