


CARBIDE, 4 FLUTE 35° HELIX SHORT LENGTH

- **VOLLHARTMETALL, 4 SCHNEIDEN 35° RECHTSSPIRALE KURZ**
- **Fraise carbure, 4 dents, hélice 35°, courte**
- **4 TAGLIENTI, ELICA 35°, CORTA**

- ▶ Ultra micro grain carbide
- ▶ Reduces chipping of corner edges
- ▶ Suitable for low hardness materials (under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steels, etc

- ▶ Ultra Feinstkorn - Vollhartmetall
- ▶ Verstärkte Schneidkante.
- ▶ Für die Bearbeitung von: Werkstoffen bis 45 HRc, rostfreien Stählen, Titan und Nickellegierungen.




CARBIDE 4 35° PLAIN FLAT P.427

Unit : mm

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	D1	D2	L1	L2
EH913020	-	2.0	4	6	40
EH913901	EH914901	2.0	6	6	40
EH913025	-	2.5	4	8	40
EH913902	EH914902	2.5	6	8	40
EH913030	EH914030	3.0	6	8	45
EH913035	EH914035	3.5	6	10	45
EH913040	EH914040	4.0	6	11	45
EH913045	EH914045	4.5	6	11	45
EH913050	EH914050	5.0	6	13	50
EH913055	EH914055	5.5	6	13	50
EH913060	EH914060	6.0	6	13	50
EH913065	EH914065	6.5	8	16	60
EH913070	EH914070	7.0	8	16	60
EH913075	EH914075	7.5	8	16	60
EH913080	EH914080	8.0	8	19	60
EH913085	EH914085	8.5	10	19	70
EH913090	EH914090	9.0	10	19	70
EH913095	EH914095	9.5	10	19	70
EH913100	EH914100	10.0	10	22	70
EH913110	EH914110	11.0	12	22	75

▶ NEXT PAGE

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5



◎ : Excellent ○ : Good


ISO Material Description	P											M				K					
	Non-alloy steel					Low alloy steel				High alloyed steel, and tool steel		Stainless steel			Grey cast iron		Nodular cast iron		Malleable cast iron		
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	
HRc		13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25		21	
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230	
Recommend	○	○	◎	◎	◎	○	◎	◎	◎	○	◎	○	○	◎							
ISO Material Description	N										S						H				
	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)			Non Metallic Materials		Heat Resistant Super Alloys						Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommend																◎	◎			○	

CARBIDE, 4 FLUTE 35° HELIX SHORT LENGTH

- VOLLHARTMETALL, 4 SCHNEIDEN 35° RECHTSSPIRALE KURZ
- ⊕ Fraise carbure, 4 dents, hélice 35°, courte
- ⊕ 4 TAGLIENTI, ELICA 35°, CORTA

- ▶ Ultra micro grain carbide
- ▶ Reduces chipping of corner edges
- ▶ Suitable for low hardness materials(under HRc45), alloy steels, tool steels, carbon steels, prehardened steels, stainless steels, etc

- ▶ Ultra Feinstkorn - Vollhartmetall
- ▶ Verstärkte Schneidkante.
- ▶ Für die Bearbeitung von: Werkstoffen bis 45 HRc, rostfreien Stählen, Titan und Nickellegierungen.




CARBIDE 4 35° PLAIN FLAT P.427

Unit : mm

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	D1	D2	L1	L2
EH913120	EH914120	12.0	12	26	75
EH913140	EH914140	14.0	16	26	85
EH913160	EH914160	16.0	16	32	100
EH913180	EH914180	18.0	16	32	100
EH913200	EH914200	20.0	20	38	105
EH913220	EH914220	22.0	20	38	105
EH913250	EH914250	25.0	25	45	120

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5



Enforced Cutting Edge

◎ : Excellent ○ : Good


ISO Material Description	P										M				K						
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel				Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	
HRc																					
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230	
Recommend	○	○	◎	◎	◎	○	◎	◎	◎	○	◎	○	○	◎	○	○	○	○	○	○	
ISO Material Description	N					S					H										
	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)			Non Metallic Materials		Heat Resistant Super Alloys			Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc																					
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommend																◎	◎			○	

EH913, EH914 SERIES

4 FLUTE - SIDE CUTTING

Vc = m/min.
fz = mm/tooth
RPM = rev./min.
FEED = mm/min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)										
						2.0	3.0	4.0	5.0	6.0	8.0	10.0	12.0	16.0	20.0	25.0
P	1-4	Non-alloy steel	0.05D	1.0D	Vc	75	85	95	100	105	105	100	105	110	105	105
					fz	0.006	0.009	0.019	0.024	0.03	0.042	0.047	0.047	0.047	0.048	0.046
	RPM		11937	9019	7560	6366	5570	4178	3183	2785	2188	1671	1337			
	FEED		286	325	575	611	668	702	598	524	411	321	246			
	Vc		50	50	60	60	65	65	65	65	70	65	65			
	fz		0.006	0.009	0.019	0.024	0.031	0.038	0.038	0.037	0.037	0.038	0.039			
	RPM	7958	5305	4775	3820	3448	2586	2069	1724	1393	1035	828				
	FEED	191	191	363	367	428	393	314	255	206	157	129				
	5	Low alloy steel	0.05D	1.0D	Vc	75	85	95	100	105	105	100	105	110	105	105
					fz	0.006	0.009	0.019	0.024	0.03	0.042	0.047	0.047	0.047	0.048	0.046
	RPM		11937	9019	7560	6366	5570	4178	3183	2785	2188	1671	1337			
	FEED		286	325	575	611	668	702	598	524	411	321	246			
Vc	50		50	60	60	65	65	65	65	70	65	65				
fz	0.006		0.009	0.019	0.024	0.031	0.038	0.038	0.037	0.037	0.038	0.039				
RPM	7958	5305	4775	3820	3448	2586	2069	1724	1393	1035	828					
FEED	191	191	363	367	428	393	314	255	206	157	129					
6-7	High alloyed steel, and tool steel	0.05D	1.0D	Vc	75	85	95	100	105	105	100	105	110	105	105	
				fz	0.006	0.009	0.019	0.024	0.03	0.042	0.047	0.047	0.047	0.048	0.046	
RPM		11937	9019	7560	6366	5570	4178	3183	2785	2188	1671	1337				
FEED		286	325	575	611	668	702	598	524	411	321	246				
Vc		50	50	60	60	65	65	65	65	70	65	65				
fz		0.006	0.009	0.019	0.024	0.031	0.038	0.038	0.037	0.037	0.038	0.039				
RPM	7958	5305	4775	3820	3448	2586	2069	1724	1393	1035	828					
FEED	191	191	363	367	428	393	314	255	206	157	129					
8-9	Stainless steel	0.05D	1.0D	Vc	75	85	95	100	105	105	100	105	110	105	105	
				fz	0.006	0.009	0.019	0.024	0.03	0.042	0.047	0.047	0.047	0.048	0.046	
RPM		11937	9019	7560	6366	5570	4178	3183	2785	2188	1671	1337				
FEED		286	325	575	611	668	702	598	524	411	321	246				
Vc		50	50	60	60	65	65	65	65	70	65	65				
fz		0.006	0.009	0.019	0.024	0.031	0.038	0.038	0.037	0.037	0.038	0.039				
RPM	7958	5305	4775	3820	3448	2586	2069	1724	1393	1035	828					
FEED	191	191	363	367	428	393	314	255	206	157	129					
10	Titanium Alloys	0.05D	1.0D	Vc	40	45	50	50	55	55	55	50	55	55	55	
				fz	0.006	0.009	0.018	0.024	0.029	0.042	0.045	0.044	0.047	0.045	0.044	
RPM		6366	4775	3979	3183	2918	2188	1751	1326	1094	875	700				
FEED		153	172	286	306	338	368	315	233	206	158	123				
Vc		40	45	50	50	55	55	55	50	55	55	55				
fz		0.006	0.009	0.018	0.024	0.029	0.042	0.045	0.044	0.047	0.045	0.044				
RPM	6366	4775	3979	3183	2918	2188	1751	1326	1094	875	700					
FEED	153	172	286	306	338	368	315	233	206	158	123					
11.1 11.2	Chilled Cast Iron	0.05D	1.0D	Vc	50	50	60	60	65	65	65	65	70	65	65	
				fz	0.006	0.009	0.019	0.024	0.031	0.038	0.038	0.037	0.037	0.038	0.039	
RPM		7958	5305	4775	3820	3448	2586	2069	1724	1393	1035	828				
FEED		191	191	363	367	428	393	314	255	206	157	129				
Vc		40	45	50	50	55	55	55	50	55	55	55				
fz		0.006	0.009	0.018	0.024	0.029	0.042	0.045	0.044	0.047	0.045	0.044				
RPM	6366	4775	3979	3183	2918	2188	1751	1326	1094	875	700					
FEED	153	172	286	306	338	368	315	233	206	158	123					
M	14.1	0.05D	1.0D	Vc	40	45	50	50	55	55	55	50	55	55	55	
				fz	0.006	0.009	0.018	0.024	0.029	0.042	0.045	0.044	0.047	0.045	0.044	
RPM		6366	4775	3979	3183	2918	2188	1751	1326	1094	875	700				
FEED		153	172	286	306	338	368	315	233	206	158	123				
Vc		40	45	50	50	55	55	55	50	55	55	55				
fz		0.006	0.009	0.018	0.024	0.029	0.042	0.045	0.044	0.047	0.045	0.044				
RPM	6366	4775	3979	3183	2918	2188	1751	1326	1094	875	700					
FEED	153	172	286	306	338	368	315	233	206	158	123					
36-37	40	0.05D	1.0D	Vc	50	50	60	60	65	65	65	65	70	65	65	
				fz	0.006	0.009	0.019	0.024	0.031	0.038	0.038	0.037	0.037	0.038	0.039	
RPM		7958	5305	4775	3820	3448	2586	2069	1724	1393	1035	828				
FEED		191	191	363	367	428	393	314	255	206	157	129				
Vc		40	45	50	50	55	55	55	50	55	55	55				
fz		0.006	0.009	0.018	0.024	0.029	0.042	0.045	0.044	0.047	0.045	0.044				
RPM	6366	4775	3979	3183	2918	2188	1751	1326	1094	875	700					
FEED	153	172	286	306	338	368	315	233	206	158	123					



SELECTION GUIDE



SERIES	EH911 EH912	EH913 EH914	EH830 EH840
FLUTE	2	4	3&4
HELIX ANGLE	35°	35°	50°
CUTTING EDGE SHAPE	SQUARE	SQUARE	SQUARE
SIZE MIN	D1.0	D2.0	D6.0
SIZE MAX	D25.0	D25.0	D25.0
PAGE	414	416	418

SOLID CARBIDE
JET-POWER
END MILLS

Exotic materials like Stainless Steels
Nickel alloys and Titanium



Please visit
globalyg1.com/mat
for material search

◎ : Excellent ○ : Good

Recommended cutting conditions : P 426

ISO	VDI 3323	Material Description	Composition / Structure / Heat Treatment	HB	HRc				
P	1	Non-alloy steel	About 0.15% C Annealed	125		○	○	○	
	2		About 0.45% C Annealed	190	13	○	○	○	
	3		About 0.45% C Quenched & Tempered	250	25	◎	◎	◎	
	4		About 0.75% C Annealed	270	28	◎	◎	◎	
	5		About 0.75% C Quenched & Tempered	300	32	◎	◎	◎	
	6	Low alloy steel	Annealed	180	10	○	○	○	
	7		Quenched & Tempered	275	29	◎	◎	◎	
	8		Quenched & Tempered	300	32	◎	◎	◎	
	9		Quenched & Tempered	350	38	◎	◎	◎	
	10		High alloyed steel, and tool steel	Annealed	200	15	○	○	○
	11			Quenched & Tempered	325	35	◎	◎	◎
M	12	Stainless steel	Ferritic / Martensitic Annealed	200	15	○	○	○	
	13		Martensitic Quenched & Tempered	240	23	○	○	○	
	14		Austenitic	180	10	◎	◎	◎	
K	15	Grey cast iron	Pearlitic / ferritic	180	10				
	16		Pearlitic (Martensitic)	260	26				
	17	Nodular cast iron	Ferritic	160	3				
	18		Pearlitic	250	25				
	19		Ferritic	130					
20	Malleable cast iron	Pearlitic	230	21					
N	21	Aluminum-wrought alloy	Not Curable	60					
	22		Curable Hardened	100					
	23	Aluminum-cast, alloyed	≤ 12% Si, Not Curable	75					
	24		≤ 12% Si, Curable Hardened	90					
	25		> 12% Si, Not Curable	130					
	26	Copper and Copper Alloys (Bronze / Brass)	Cutting Alloys, PB>1%	110					
	27		CuZn, CuSnZn (Brass)	90					
	28		CuSn, lead-free copper and electrolytic copper	100					
	29	Non Metallic Materials	Duroplastic, Fiber Reinforced Plastic						
	30		Rubber, Wood, etc.						
S	31	Heat Resistant Super Alloys	Fe Based Annealed	200	15			○	
	32		Cured	280	30			○	
	33		Annealed	250	25			○	
	34		Ni or Co Based Cured	350	38			○	
	35		Cast	320	34			○	
	36	Titanium Alloys	Pure Titanium	400 Rm		◎	◎	◎	
	37		Alpha + Beta Alloys Hardened	1050 Rm		◎	◎	◎	
H	38	Hardened steel	Hardened	550	55				
	39		Hardened	630	60				
	40	Chilled Cast Iron	Cast	400	42	○	○	○	
	41	Hardened Cast Iron	Hardened	550	55				