

THREAD MILLS

SYNCHRO TAPS

COMBO TAPS

YG TAP GENERAL

YG TAP STEEL

YG TAP HARDENED

YG TAP INOX

YG TAP CAST IRON

YG TAP ALU

YG TAP Ti Ni

YG TAP FORMING

NUT TAPS

STI TAPS

PIPE TAPS



TECHNICAL DATA

**M ISO metric coarse threads DIN 13**

- 🇩🇪 **Metrisches ISO-Gewinde DIN 13**
- 🇫🇷 **ISO MÉTRIQUE DIN13**
- 🇮🇹 **ISO Metrico passo grosso DIN 13**

- ▶ Coated HSS-PM(Powder Metallurgy) Taps for high-speed tapping on rigid CNC machines or equivalent machines
- ▶ Up to 3 times faster in tapping compared to conventional taps
- ▶ For high-speed synchro tapping, synchro holder for increasing tool life and thread quality is recommended
- ▶ High precision threads

- ▶ Beschichtete HSS-PM-Gewindebohrer zum Hochgeschwindigkeitsgewindebohren auf starren CNC-Maschinen oder gleichwertige Maschinen
- ▶ Bis zu dreimal schnelleres Gewindeschneiden als bei herkömmlichen Gewindebohrern
- ▶ Beim Hochgeschwindigkeits-Gewindebohren wird die Verwendung eines Synchrofußers zur Erhöhung der Werkzeugstandzeit und der Gewindequalität empfohlen
- ▶ Hoch präzise Gewinde



Material groups: **GV** **HSS-PM** **DIN 371/376** **6HX** **60°** **C** **TiN**

Cold forming taps  
Gewindeformer

Recommended cutting : P.69

Unit : mm

SIZE	Pitch	EDP No.	Thread Length	Overall Length	Neck Length	Shank Diameter	Square Size	Square Length	Tapping Drill Diameter
ØD1	P	TiN	L1	L2	L3	ØD2	K	KI	Ød1
M3	× 0.5	<b>TTS37206</b>	5	56	18	3.5	2.7	6	2.8
M4	× 0.7	<b>TTS37246</b>	7	63	21	4.5	3.4	6	3.7
M5	× 0.8	<b>TTS37286</b>	8	70	25	6	4.9	8	4.65
M6	× 1	<b>TTS37316</b>	10	80	30	6	4.9	8	5.55
M8	× 1.25	<b>TTS37366</b>	13	90	35	8	6.2	9	7.4
M10	× 1.5	<b>TTS37426</b>	15	100	39	10	8	11	9.3
M12	× 1.75	<b>TTS37506</b>	18	110	44	9	7	10	11.2

▶DIN 371(M3~M10) and DIN 376(M11~M12)

◎ : Excellent ○ : Good

ISO	P										M				K					
	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel		Stainless steel		Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20
HRc	13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25		21	
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	260	160	250	130	230	
Recommended	◎	◎	◎	◎	◎	◎	◎				◎	◎	◎							

ISO	N					S					H										
	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)		Non Metallic Materials			Heat Resistant Super Alloys			Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRc											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400Rm	1050Rm	550	630	400	550
Recommended	◎	◎	◎	◎	○			◎													

ISO	VDI 3323	Material Description	HB	HRc	TTS31	TTS33	TKS35	TTS37
					Vc (m/min)			
P	1	Non-alloy steel	125		41-46	41-46	41-46	41-46
	2		190	13	41-46	41-46	41-46	41-46
	3		250	25	35-40	35-40	35-40	35-40
	4		270	28	28-33	28-33	28-33	28-33
	5		300	32				
	6	Low alloy steel	180	10	28-33	28-33	28-33	28-33
	7		275	29	28-33	28-33	28-33	28-33
	8		300	32				
	9		350	38				
	10	High alloyed steel, and tool steel	200	15				
	11		325	35				
M	12	Stainless steel	200	15	18-23	18-23		18-23
	13		240	23	13-18	13-18		13-18
	14		180	10	10-14	10-14		10-14
K	15	Grey cast iron	180	10	28-33	28-33	28-33	
	16		260	26			13-18	
	17	Nodular cast iron	160	3	28-33	28-33	28-33	
	18		250	25			13-18	
	19	Malleable cast iron	130				28-33	
	20		230	21			13-18	
N	21	Aluminum- wrought alloy	60					28-33
	22		100					28-33
	23	Aluminum- cast, alloyed	75		41-46	41-46	41-46	41-46
	24		90		41-46	41-46	41-46	41-46
	25		130		30-35	30-35	30-35	30-35
	26		110		45-50	45-50		
	27	Copper and Copper Alloys (Bronze / Brass)	90					
	28		100		25-30	25-30		25-30
	29							
	30	Non Metallic Materials						
S	31	Heat Resistant Super Alloys	200	15				
	32		280	30				
	33		250	25				
	34		350	38				
	35		320	34				
	36	Titanium Alloys	400 Rm					
	37		1050 Rm					
H	38	Hardened steel	550	55				
	39		630	60				
	40	Chilled Cast Iron	400	42				
	41	Hardened Cast Iron	550	55				

# SURFACE TREATMENT AND COATING

The applied High Speed Steels holds a grant of good wear resistance and toughness. Therefore YG-1 normally delivers taps with bright and unfinished surface. For certain materials, various surface treatments provide higher advantage in machining.

## STEAM TEMPERED - Vap

Steam Tempered is a Fe<sub>3</sub>O<sub>4</sub>-oxyd-coating which reduces friction between the tool and workpiece, also preventing cold welding.

## NITRIDING - NI

Recommend surface treatment for machining materials that affect wear abrasion, such as grey cast iron, alu-alloys with high Si-percentages (more than 10%).

Below are the various surface treatments for excellent finish surfaces suitable for many applications. The surface treatments are produced and developed within the company.

## TiN-COATING

TiN-coating yields a hardness of approx. 2,300 HV and also a heat resistant up to approx. 600°C. The current coating is an excellent all-round coating for normal applications.

Colour : Golden Coefficient of friction against steel : 0.4

## TiCN-COATING

TiCN takes place of TiN when the conditions require the coating to have a different hardness and toughness.

The TiCN brings advantages for machining very difficult steels or cutting interrupted bores.

The TiCN-coating has a hardness of approx. 3,000 HV, but is heat resistance only holds up to approx. 400°C, meaning that the TiCN needs an excellent cooling system for a long service life.

Colour : Blue-Grey Coefficient of friction against steel : 0.4

## TiAlN-COATING

A special coating for machining abrasive materials such as grey cast iron, alu-alloys with silicon, fiber reinforced plastics, etc., or machining at high temperatures with insufficient cooling, or at high speeds  $\geq 600$ m/min. TiAlN has a hardness of approx. 3,000 HV and is heat resistant up to approx. 800°C.

Colour : Violet-Grey Coefficient of friction against steel : 0.4

## Hardslick-COATING

Hardslick combines the advantages of an extremely hard, thermally stable TiAlN-coating with the sliding and lubricating properties of an outer WC/C(Tungsten carbide/carbon)-coating in a novel way. The Hardslick coating has a hardness of approx. 3,000 HV and is temperature-resistant up to approx. 800°C.

Colour : Violet-Grey Coefficient of friction against steel : 0.2

SELECTION GUIDE



# HSS-PM SYNCHRO TAPS

For High Speed Tapping on Rigid CNC Machine

HOLE TYPE		Max. 2.5xD	Max. 3.0xD	Max. 2.0xD	Max. 3.0xD	
TOOL MATERIAL		HSS-PM				
CHAMFER LEAD ACC. TO DIN2197		C	B	C	C	
FLUTE TYPE		Spiral Flute	Spiral Point	Straight Flute	Cold Forming	
SPIRAL FLUTE ANGLE		R45	-	-	-	
SERIES	M	DIN371/376	TTS31 (P65)	TTS33 (P66)	TKS35 (P67)	TTS37 (P68)
		DIN352				
		DIN357/LONG				
	MF	DIN374				
		DIN2181				
	UNC	DIN371/376				
		DIN351				
	UNF	DIN371/374				
		DIN2181				
	BSW	DIN2182/2183				
		DIN351				
	G(BSP)	DIN5156/5157				
	EG-M	DIN371/376				
	EG-UNC	DIN371/376				
EG-UNF	DIN371/374					
SURFACE TREATMENT		TIN	TIN	TiCN	TIN	
MODEL						



Please visit [globalyg1.com/mat](http://globalyg1.com/mat) for material search

◎ : Excellent ○ : Good

Recommended cutting conditions : P.69

ISO	VDI 3323	Material Description	Composition / Structure / Heat Treatment	HB	HRc	TIN	TIN	TiCN	TIN
P	1	Non-alloy steel	About 0.15% C Annealed	125		◎	◎	○	◎
	2		About 0.45% C Annealed	190	13	◎	◎	○	◎
	3		About 0.45% C Quenched & Tempered	250	25	◎	◎	○	◎
	4	Low alloy steel	About 0.75% C Annealed	270	28	◎	◎	○	◎
	5		About 0.75% C Quenched & Tempered	300	32				
	6		Annealed	180	10	◎	◎	○	◎
	7		Quenched & Tempered	275	29	◎	◎	○	◎
	8	High alloyed steel, and tool steel	Quenched & Tempered	300	32				
	9		Quenched & Tempered	350	38				
	10		Annealed	200	15				
	11	Quenched & Tempered	325	35					
M	12	Stainless steel	Ferritic / Martensitic Annealed	200	15	◎	◎		◎
	13		Martensitic Quenched & Tempered	240	23	◎	◎		◎
	14		Austenitic	180	10	○	○		◎
K	15	Grey cast iron	Pearlitic / ferritic	180	10	○	○	◎	
	16		Pearlitic (Martensitic)	260	26			◎	
	17	Nodular cast iron	Ferritic	160	3	◎	◎	◎	
	18		Pearlitic	250	25			◎	
	19	Malleable cast iron	Ferritic	130				○	
	20		Pearlitic	230	21			○	
N	21	Aluminum-wrought alloy	Not Curable	60					◎
	22		Curable Hardened	100					◎
	23	Aluminum-cast, alloyed	≤ 12% Si, Not Curable	75		◎	◎	○	◎
	24		≤ 12% Si, Curable Hardened	90		◎	◎	○	◎
	25		> 12% Si, Not Curable	130		◎	◎	○	○
	26		Cutting Alloys, PB>1%	110		◎	◎		
	27	Copper and Copper Alloys (Bronze / Brass)	CuZn, CuSnZn (Brass)	90					
	28		CuSn, lead-free copper and electrolytic copper	100		○	○		◎
	29	Non Metallic Materials	Duroplastic, Fiber Reinforced Plastic						
	30		Rubber, Wood, etc.						
S	31	Heat Resistant Super Alloys	Fe Based Annealed	200	15				
	32		Cured	280	30				
	33		Annealed	250	25				
	34		Ni or Co Based Cured	350	38				
	35		Cast	320	34				
	36	Titanium Alloys	Pure Titanium	400 Rm					
	37		Alpha + Beta Alloys Hardened	1050 Rm					
H	38	Hardened steel	Hardened	550	55				
	39		Hardened	630	60				
	40	Chilled Cast Iron	Cast	400	42				
	41	Hardened Cast Iron	Hardened	550	55				