End mill High-performance machining

PM-4H



– Factory standard
– Centre cutting
– Helix angle 0°



Article	✻	Dimensions [mm]							Teeth	Geometry	Grade
		R	D	d (h6)	d_1	H	M	L			KMG405
PM-4H-D3.0R0.8		0.8	3	6	2.7	1.2	8	50	4	A	●
PM-4H-D4.0R1.0		1	4	6	3.6	1.6	10	50	4	A	●
PM-4H-D5.0R1.2		1.2	5	6	4.5	2	12.5	50	4	A	●
PM-4H-D6.0R1.0		1	6	6	5.4	2.5	12	50	4	B	●
PM-4H-D6.0R1.5		1.5	6	6	5.4	2.5	12	50	4	B	●
PM-4H-D6.0R2.0		2	6	6	5.4	2.5	12	50	4	B	●
PM-4H-D8.0R1.0		1	8	8	7	3.5	16	60	4	B	●
PM-4H-D8.0R2.0		2	8	8	7	3.5	16	60	4	B	●
PM-4H-D10.0R1.0		1	10	10	9	4	20	75	4	B	●
PM-4H-D10.0R2.0		2	10	10	9	4	20	75	4	B	●
PM-4H-D10.0R3.0		3	10	10	9	4	20	75	4	B	●
PM-4H-D12.0R2.0		2	12	12	11	5	24	75	4	B	●
PM-4H-D12.0R3.0		3	12	12	11	5	24	75	4	B	●

● Ex stock ○ On demand
✻ With internal cooling

Application field

P	M	K	N	S	H
✔	✔	✔			✔

✔ Very suitable
✔ Suitable

System code B268 Cutting data B436 Nonstandard order B477

End mill – PM series

Material group		Composition / structure / heat treatment		Brinell hardness HB	Machining group	Starting values for cutting speed v_c [m/min]							
						PM-2R PM-4R				PM-4RL			
						Slot milling		Shoulder milling		Slot milling		Shoulder milling	
						Ø [mm]	$a_{p\,max}$	Ø [mm]	$a_{e\,max}$	Ø [mm]	$a_{p\,max}$	Ø [mm]	$a_{e\,max}$
						0 < x < 3	0,1 5x D	0 < x ≤ 20	0.15 x D	0 < x < 3	0,1 5x D	0 < x ≤ 20	0.15 x D
						3 ≤ x < 6	0,3 x D			3 ≤ x < 6	0,3 x D		
						6 ≤ x ≤ 20	0,5 x D			6 ≤ x ≤ 20	0,5 x D		
						KMG405				KMG405			
						a_e / D				a_e / D			
						1/1	1/2	1/10	f-group	1/1	1/2	1/10	f-group
P	Unalloyed steel	approx. 0,15 % C	annealed	125	1	165	220	300	1	150	200	265	1
		approx. 0,45 % C	annealed	190	2	160	210	285	1	145	190	255	1
		approx. 0,45 % C	tempered	250	3	120	155	210	1	105	140	190	1
		approx. 0,75 % C	annealed	270	4	100	135	180	1	90	120	160	1
		approx. 0,75 % C	tempered	300	5	95	125	165	1	85	110	150	1
	Low-alloyed steel		annealed	180	6	125	165	225	1	115	150	200	1
			tempered	275	7	100	135	180	1	90	120	160	1
			tempered	300	8	95	125	165	1	85	110	150	1
			tempered	350	9	90	115	160	1	80	105	140	1
	High-alloyed steel and high-alloyed tool steel		annealed	200	10	120	155	210	1	105	140	190	1
			hardened and tempered	325	11	90	120	160	1	80	110	145	1
M	Stainless steel	ferritic/martensitic	annealed	200	12	55	75	100	1	50	65	85	1
		martensitic	tempered	240	13	50	65	85	1	45	60	75	1
		austenitic	quench hardened	180	14	60	75	105	1	55	70	95	1
		austenitic-ferritic		230	15	50	65	85	1	45	60	75	1
K	Grey cast iron	perlitic/ferritic		180	16	125	165	220	1	110	150	195	1
		perlitic (martensitic)		260	17	100	135	180	1	90	120	160	1
	Cast iron with spheroidal graphite	ferritic		160	18	150	200	270	1	135	180	240	1
		perlitic		250	19	120	155	210	1	105	140	190	1
	Malleable cast iron	ferritic		130	20	165	220	300	1	150	200	265	1
		perlitic		230	21	135	180	240	1	120	160	215	1
N	Aluminium wrought alloys	cannot be hardened		60	22								
		hardenable	hardened	100	23								
	Cast aluminium alloys	≤ 12 % Si, cannot be hardened		75	24								
		≤ 12 % Si, hardenable	hardened	90	25								
		> 12 % Si, cannot be hardened		130	26								
	Copper and copper alloys (bronze/brass)	machining steel, PB> 1%		110	27								
		CuZn, CuSnZn		90	28								
		CuSn, Pb-free copper, electrolytic copper		100	29								
S	Heat-resistant alloys	Fe-based alloys	annealed	200	30								
			hardened	280	31								
		Ni or Co bass	annealed	250	32								
			hardened	350	33								
			cast	320	34								
	Titanium alloys	pure titanium		R_m 400	35								
		α and β alloys	hardened	R_m 1050	36								
H	Hardened steel		hardened and tempered	55 HRC	37	85	110	145	1	70	95	125	1
			hardened and tempered	60 HRC	38								
	Hard cast iron		cast	400	39	115	145	190	1	95	125	165	1
	Hardened cast iron		hardened and tempered	55 HRC	40								
X	Non-metallic materials	Thermoplasts			41								
		Thermosetting plastics			42								
		Plastic, glass-fibre reinforced GFRP			43								
		Plastic, carbon fibre reinforced CFRP			44								
		Graphite			45								
		Wood			46								

Note: The given cutting values are guide values, which were determined under ideal conditions.
The values have to be adapted in individual cases.
Feed rate recommendations on page B460.
For examples of material for cutting tool groups view page D22.

	Starting values for cutting speed v_c [m/min]				
	PM-4H PM-4HL				
			Shoulder milling		
			Ø [mm]	$a_{e\,max}$	
			0 < x ≤ 20	0.15 x D	
	KMG405				
	a_e / D				
	1/1	1/2	1/10	f-group	
		210	270	6	
		200	260	6	
		150	190	6	
		130	165	6	
		120	150	6	
		160	205	6	
		130	165	6	
		120	150	6	
		110	145	6	
		150	190	6	
		115	145	6	
		70	90	6	
		60	80	6	
		75	95	6	
		60	80	6	
		155	200	6	
		130	165	6	
		190	245	6	
		150	190	6	
		210	270	6	
		170	220	6	
		100	125	1	
		130	165	1	

Recommended feed rate

Solid carbide milling group 5 – Ball nose cutters GM series

	a_e / D	Feed rate per cutting edge (f_z) [mm]																			
		Ø0,5	Ø0,8	Ø 1	Ø 2	Ø 3	Ø 4	Ø 5	Ø 6	Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 18	Ø 20					
P	1/1																				
	1/10	0,02	0,05	0,05	0,05	0,05	0,05	0,07	0,07	0,09	0,14	0,16	0,16	0,18	0,18	0,20					
	1/20	0,03	0,06	0,06	0,06	0,06	0,06	0,08	0,08	0,11	0,17	0,20	0,20	0,23	0,23	0,25					
M	1/1																				
	1/10	0,02	0,04	0,04	0,04	0,04	0,04	0,05	0,05	0,07	0,11	0,13	0,13	0,15	0,15	0,16					
	1/20	0,02	0,05	0,05	0,05	0,05	0,05	0,07	0,07	0,09	0,14	0,16	0,16	0,18	0,18	0,21					
K	1/1																				
	1/10	0,02	0,05	0,05	0,05	0,05	0,05	0,07	0,07	0,09	0,14	0,16	0,16	0,18	0,18	0,20					
	1/20	0,03	0,06	0,06	0,06	0,06	0,06	0,08	0,08	0,11	0,17	0,20	0,20	0,23	0,23	0,25					
H	1/1																				
	1/10	0,02	0,04	0,04	0,04	0,04	0,04	0,05	0,05	0,07	0,11	0,13	0,13	0,15	0,15	0,16					
	1/20	0,02	0,05	0,05	0,05	0,05	0,05	0,07	0,07	0,09	0,14	0,16	0,16	0,18	0,18	0,21					

Note: The given cutting values are guide values, which were determined under ideal conditions.
The values have to be adapted in individual cases.

Solid carbide milling group 6 – High feed mills PM series

	a_e / D	Feed rate per cutting edge (f_z) [mm]																			
		Ø 3	Ø 4	Ø 5	Ø 6	Ø 8	Ø 10	Ø 12													
P	1/1																				
	1/10																				
	1/20	0,15	0,25	0,28	0,33	0,44	0,55	0,66													
M	1/1																				
	1/10																				
	1/20	0,12	0,22	0,25	0,30	0,41	0,52	0,63													
K	1/1																				
	1/10																				
	1/20	0,15	0,25	0,28	0,33	0,44	0,55	0,66													
H	1/1																				
	1/10																				
	1/20	0,12	0,22	0,25	0,30	0,41	0,52	0,63													

Note: The given cutting values are guide values, which were determined under ideal conditions.
The values have to be adapted in individual cases.

Solid carbide milling group 7 – Ball nose cutters HM series

	a_e / D	Feed rate per cutting edge (f_z) [mm]																			
		Ø0,5	Ø0,8	Ø 1	Ø 2	Ø 3	Ø 4	Ø 5	Ø 6	Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 18	Ø 20					
H	1/1																				
	1/2	0,02	0,04	0,04	0,04	0,04	0,04	0,05	0,05	0,07	0,11	0,13	0,13	0,15	0,15	0,16					
	1/10	0,02	0,05	0,05	0,05	0,05	0,05	0,07	0,07	0,09	0,14	0,16	0,16	0,18	0,18	0,21					

Note: The given cutting values are guide values, which were determined under ideal conditions.
The values have to be adapted in individual cases.

Solid carbide milling group 8 – High feed mills AL series

	a_e / D	Feed rate per cutting edge (f_z) [mm]																			
		Ø 6	Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 18	Ø 20												
N	1/1	0,04	0,05	0,08	0,09	0,11	0,13	0,16	0,18												
	3/4	0,05	0,07	0,10	0,12	0,14	0,16	0,20	0,23												
	1/10	0,08	0,11	0,16	0,19	0,22	0,25	0,31	0,36												

Note: The given cutting values are guide values, which were determined under ideal conditions.
The values have to be adapted in individual cases.

PM series

For demanding applications

- For machining of steel to max. 55 HRC and cast iron to heat-resistant alloys.
- Very solid cutting edge with high stiffness for higher cutting speeds and feed rates.
- End mills, ball nose cutters, torus mills and high feed mills
- Diameter range 3.0–20.0 mm

Application fields for machining of steel



GM – 2 E L P – D12 R0.5 – M08 – W

1	2	3	4	5	6	7	8	9

Application	
Code	Description
GR	General roughing
GM	Semi-finishing
GF	Finishing
PM	High-performance machining
HM	Hard machining
HH	High-speed hard machining
NM	General machining of non-ferrous metals
AL	General machining of Al and Al alloys
ALP	High-performance machining of Al and Al alloys
ALG	General machining of Al and Al alloys
UM	HSC/HPC machining
VSM	General machining of heat-resistant alloys

1

Number of teeth

2

Cutting edge type	
Code	Description
E	Square shoulder mill with protective chamfer
F	Square shoulder mill with sharp cutting edges
B	Ball nose cutter
R	Torus mill
W	Ripper
H	High-feed mill

3

Cutting edge length	
Code	Description
L	Long
X	Extra long
F	Short

4

Type	
Code	Description
S	Mini diameter
P	Ground neck
C	Conical neck

5

Diameter [mm]	
Code	Description
D3.0	3,0
D8.0	8,0
D20.0	20,0
...	

6

Radius [mm]	
Code	Description
R0.5	0,5
R1.0	1,5
R3.0	3,0
...	

7

Features	
Code	Description
G	Spiral angle 30°
M	Neck length [mm]
S	Thin shank
AIR	For aerospace industry

8

Weldon shank

9



a Groove milling **b** Square shoulder milling **c** Profile milling **d** Slot milling **e** Face milling **f** Chamfer milling **g** Plunge milling **h** Circular milling/Ramping

Coated cemented carbide PVD

Grade	Grade description
KMD401	PVD coated carbide substrate for high performance milling application of non-ferrous metals, CFRP and GFRP and organic materials. The DLC layer has very good wear protection and high thermal stability.
KMG303	PVD coated carbide substrate for universal milling application of steel (up to HRC<=48), stainless steel and cast iron.
KMG405	PVD coated carbide substrate for high performance milling application of steel (up to HRC <55), stainless steel, super alloy material and cast iron. High wear resistance and toughness for a wide application field.
KMG555	PVD coated carbide substrate for hard milling application of steel (HRC 55–68), highest wear resistance and toughness for best cutting result.
KMG309	PVD coated carbide substrate for non ferrous materials. High wear resistance even in abrasive materials.

Uncoated cemented carbide

Grade	Grade description
YK30F	Uncoated K30 carbide substrate for steel, stainless steel, cast iron and non ferrous materials.
YK40F	Uncoated K20–K30/N20–N30 carbide substrate for cast iron and non ferrous materials.

High performance milling

Products	Solid carbide cutters	Teeth	Ø	Application						Type	Page
				P	M	K	N	S	H		
PM-2E		2	1.0-20.0	✓	✓	✓			✓	End mills	B330
PM-2EL		2	3.0-20.0	✓	✓	✓			✓	End mills	B331
PM-4E-G		4	1.0-20.0	✓	✓	✓			✓	End mills	B332
PM-4EL-G		4	3.0-20.0	✓	✓	✓			✓	End mills	B333
PM-4EX-G		4	3.0-20.0	✓	✓	✓			✓	End mills	B334
PM-4E		4	1.0-20.0	✓	✓	✓			✓	End mills	B335
PM-4EL		4	3.0-20.0	✓	✓	✓			✓	End mills	B336
PM-6E		6	6.0-20.0	✓	✓	✓			✓	End mills	B337
PM-6EL		6	6.0-20.0	✓	✓	✓			✓	End mills	B338
PM-2B		2	1.0-20.0	✓	✓	✓			✓	Ball nose cutters	B339
PM-2BL		2	2.0-20.0	✓	✓	✓			✓	Ball nose cutters	B340
PM-2BFP		2	1.0-20.0	✓	✓	✓			✓	Ball nose cutters	B341
PM-2BC		2	0.5-4.0	✓	✓	✓			✓	Ball nose cutter with conical neck	B342
PM-4B		4	3.0-20.0	✓	✓	✓			✓	Ball nose cutters	B345
PM-4BL		4	3.0-20.0	✓	✓	✓			✓	Ball nose cutters	B346
PM-2R		2	1.0-12.0	✓	✓	✓			✓	Torus mills	B347
PM-4R		4	3.0-12.0	✓	✓	✓			✓	Torus mills	B350
PM-4RL		4	6.0-16.0	✓	✓	✓			✓	Torus mills	B351
PM-4H		4	3.0-12.0	✓	✓	✓			✓	High-feed mills	B348
PM-4HL		4	4.0-12.0	✓	✓	✓			✓	High-feed mills	B349

✓ Very suitable ✓ Suitable